

What is claimed is:

1. A method for reducing the defect density of glass produced via a float glass process comprising
 - 5 a. melting a glass composition comprising:
 - from 65-75 wt.% of SiO_2 ;
 - from 10-20 wt.% of Na_2O ;
 - from 5-15 wt.% of CaO ;
 - from 0-5 wt.% of MgO ;
 - 10 from 0-5 wt.% of Al_2O_3 ;
 - from 0-5 wt.% of K_2O ;
 - from 0-2 wt.% Fe_2O_3 ; and
 - from 0-2 wt. % FeO ,wherein the glass composition has a total field strength index of greater than or equal
15 to 1.23.
2. A method according to claim 1 wherein the glass composition further comprises at least one of the following: from 0.0 to 2.0 weight percent TiO_2 based on the weight of the composition; from 0.0 to 3.0 weight percent of erbium oxide based
20 on the total weight of the composition; and/or from 0.0 to 2.0 weight percent of neodymium based on the total weight of the composition.
3. A method according to claim 1 wherein melting the glass composition yields a glass melt having a water content of at least 0.035 weight percent based on the total
25 weight percent of the composition
4. A method according to claim 1 wherein the glass produced has a defect density of less than 10 total defects per 100 square feet.
- 30 5. A float glass composition comprising:
 - from 65-75 wt.% of SiO_2 ;
 - from 10-20 wt.% of Na_2O ;
 - from 5-15 wt.% of CaO ;
 - from 0-5 wt.% of MgO ;

from 0-5 wt.% of Al_2O_3 ;
from 0-5 wt.% of K_2O ;
from 0-2 wt.% Fe_2O_3 ; and
from 0-2 wt. % FeO ,

5 wherein the glass composition has a total field strength index of greater than or equal to 1.23.

6. A float glass composition according to claim 5 further comprising at least one of the following: from 0.0 to 2.0 weight percent TiO_2 based on the weight of the
10 composition; from 0.0 to 3.0 weight percent of erbium oxide based on the total weight of the composition; and/or from 0.0 to 2.0 weight percent of neodymium based on the total weight of the composition.

7. A float glass article comprising a glass composition comprising:
15 from 65-75 wt.% of SiO_2 ;
from 10-20 wt.% of Na_2O ;
from 5-15 wt.% of CaO ;
from 0-5 wt.% of MgO ;
from 0-5 wt.% of Al_2O_3 ;
20 from 0-5 wt.% of K_2O ;
from 0-2 wt.% Fe_2O_3 ; and
from 0-2 % FeO ,

wherein the glass composition has a total field strength index of greater than or equal to 1.23.

25

8. A float glass article according to claim 7 wherein the glass composition further comprises at least one of the following: from 0.0 to 2.0 weight percent TiO_2 based on the weight of the composition; from 0.0 to 3.0 weight percent of erbium oxide based on the total weight of the composition; and/or from 0.0 to 2.0 weight percent of
30 neodymium based on the total weight of the composition

9. A float glass article according to claim 8 wherein the article comprises at least one piece of glass in a laminated product, the article contains greater than 1 total defect per 100 square feet.

10. A float glass article according to claim 8 wherein the laminated product is a windshield.